



Makrolon® Rx2530

Covestro - Polycarbonates - Polycarbonate

Wednesday, December 8, 2021

General Information

Product Description

MVR (300°C/1.2 kg) 15 cm³/10 min; medical devices; suitable for sterilization with high-energy radiation; biocompatible according to many ISO 10993-1 test requirements; medium viscosity; injection molding - melt temperature 280 - 320°C; transparent parts for medical devices

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Biocompatible	• Medium Viscosity	• Radiation Sterilizable
Uses	• Medical Devices • Medical/Healthcare Applications		
Agency Ratings	• ISO 10993-Part 1		
RoHS Compliance	• RoHS Compliant		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density (73°F (23°C))	1.20 g/cm ³	1.20 g/cm ³	ISO 1183
Apparent (Bulk) Density ²	0.66 g/cm ³	0.66 g/cm ³	ISO 60
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	16 g/10 min	16 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	15 cm ³ /10min	15 cm ³ /10min	ISO 1133
Molding Shrinkage			
Across Flow	0.60 to 0.80 %	0.60 to 0.80 %	ISO 2577
Flow	0.60 to 0.80 %	0.60 to 0.80 %	ISO 2577
Across Flow : 536°F (280°C), 0.0787 in (2.00 mm) ³	0.65 %	0.65 %	ISO 294-4
Flow : 0.0787 in (2.00 mm) ³	0.60 %	0.60 %	ISO 294-4
Water Absorption			
Saturation, 73°F (23°C)	0.30 %	0.30 %	ISO 62
Equilibrium, 73°F (23°C), 50% RH	0.12 %	0.12 %	
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	348000 psi	2400 MPa	ISO 527-1/1
Tensile Stress			ISO 527-2/50
Yield, 73°F (23°C)	9720 psi	67.0 MPa	
Break, 73°F (23°C)	10900 psi	75.0 MPa	
Tensile Strain			ISO 527-2/50
Yield, 73°F (23°C)	6.1 %	6.1 %	
Break, 73°F (23°C)	130 %	130 %	
Nominal Tensile Strain at Break			ISO 527-2/50
73°F (23°C)	> 50 %	> 50 %	
Flexural Modulus ⁴ (73°F (23°C))	348000 psi	2400 MPa	ISO 178
Flexural Stress ⁴			ISO 178
73°F (23°C)	14500 psi	100 MPa	
3.5% Strain, 73°F (23°C)	10700 psi	74.0 MPa	

Copyright ©, 2021 Avient Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Avient Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Avient Distribution Company's direct control. Avient Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

Makrolon® Rx2530

Covestro - Polycarbonates - Polycarbonate

Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Flexural Strain at Flexural Strength ⁵ 73°F (23°C)	7.0 %	7.0 %	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength ⁶ -22°F (-30°C), Complete Break 73°F (23°C), Partial Break	6.7 ft·lb/in ² 33 ft·lb/in ²	14 kJ/m ² 70 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength -76°F (-60°C) -22°F (-30°C) 73°F (23°C)	No Break No Break No Break	No Break No Break No Break	ISO 179/1eU
Notched Izod Impact Strength ⁶ -22°F (-30°C), Complete Break 73°F (23°C), Partial Break	5.7 ft·lb/in ² 31 ft·lb/in ²	12 kJ/m ² 65 kJ/m ²	ISO 180/A
Multi-Axial Instrumented Impact Energy -22°F (-30°C) 73°F (23°C)	51.6 ft·lb 44.3 ft·lb	70.0 J 60.0 J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force -22°F (-30°C) 73°F (23°C)	1390 lbf 1190 lbf	6200 N 5300 N	ISO 6603-2
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Ball Indentation Hardness	17100 psi	118 MPa	ISO 2039-1
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed 264 psi (1.8 MPa), Unannealed	273 °F 252 °F	134 °C 122 °C	ISO 75-2/B ISO 75-2/A
Glass Transition Temperature ⁷	288 °F	142 °C	ISO 11357-2
Vicat Softening Temperature -- --	288 °F 286 °F	142 °C 141 °C	ISO 306/B120 ISO 306/B50
Ball Pressure Test (270°F (132°C))	Pass	Pass	IEC 60695-10-2
CLTE Flow : 73 to 131°F (23 to 55°C) Transverse : 73 to 131°F (23 to 55°C)	3.6E-5 in/in/°F 3.6E-5 in/in/°F	6.5E-5 cm/cm/°C 6.5E-5 cm/cm/°C	ISO 11359-2
Thermal Conductivity ⁸ (73°F (23°C))	1.4 Btu·in/hr/ft ² /°F	0.20 W/m/K	ISO 8302
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+16 ohms	1.0E+16 ohms	IEC 60093
Volume Resistivity (73°F (23°C))	1.0E+16 ohms·cm	1.0E+16 ohms·cm	IEC 60093
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Oxygen Index ⁹	27 %	27 %	ISO 4589-2
Flash Ignition Temperature	896 °F	480 °C	ASTM D1929
Self Ignition Temperature	1022 °F	550 °C	ASTM D1929
Additional Information	Typical Value (English)	Typical Value (SI)	
ISO Shortname	ISO 7391-PC,M, (,)-18-9	ISO 7391-PC,M, (,)-18-9	

Copyright ©, 2021 Avient Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Avient Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Avient Distribution Company's direct control. Avient Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

Makrolon® Rx2530

Covestro - Polycarbonates - Polycarbonate

Processing Information		
Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature - Dry Air Dryer	248 °F	120 °C
Drying Time - Dry Air Dryer	2.0 to 3.0 hr	2.0 to 3.0 hr
Suggested Max Moisture	< 0.020 %	< 0.020 %
Suggested Shot Size	30 to 70 %	30 to 70 %
Rear Temperature	482 to 500 °F	250 to 260 °C
Middle Temperature	518 to 536 °F	270 to 280 °C
Front Temperature	536 to 554 °F	280 to 290 °C
Nozzle Temperature	554 to 572 °F	290 to 300 °C
Processing (Melt) Temp	536 to 608 °F	280 to 320 °C
Mold Temperature	176 to 248 °F	80 to 120 °C
Back Pressure	725 to 2180 psi	5.00 to 15.0 MPa
Vent Depth	9.8E-4 to 3.0E-3 in	0.025 to 0.075 mm

Injection Notes

Standard Melt Temperature: 300°C

Peripheral Screw Speed: 0.05 - 0.2 m/s

Hold Pressure (% of Injection Pressure): 50 - 75%

Notes

¹ Typical properties: these are not to be construed as specifications.

² Pellets

³ 60x60x2mm, 500 bar

⁴ 0.079 in/min (2.0 mm/min)

⁵ 2.0 mm/min

⁶ 3.0 mm

⁷ 10°C/min

⁸ Across Flow

⁹ Procedure A