# STEREOLITHOGRAPHY CERAMIC-LIKE WHITE

(ADVANCED HIGH TEMP) Current Supplier Material: PerFORM



#### **PRODUCT DESCRIPTION**

Ceramic-Like White (Advanced High Temp) combines superior high heat tolerance with strength and stiffness. A thermal post-cure can be used to further improve mechanical properties and its heat resistance, however, it will be more brittle.

# APPLICATIONS

Advanced Ceramic-Like High-Temp White is often used for automotive housings, electrical casings, wind tunnel testing, and other components that require high heat tolerance and strength.



- High strength and stiffness
- Superior heat tolerance

## PROPERTIES

PROPERTY	TEST METHOD	VALUE	AFTER OPTIONAL THERMAL POST-CURING
Color	-	White	White
Density in solid state*	@ 25 °C (77 °F)	1.61 g/cm <sup>3</sup>	-
Water absorption (20 °C, 50% relative humidity)	ASTM D570	0.35 ± 0.15%	0.35 ± 0.15%
E-module (x-y plane)	ASTM D638, test speed 10mm/min.	10,000 ± 1,000 MPa	10,500 ± 1,000 MPa
Tensile strength (x-y plane)		70 ± 10 MPa	75 ± 10 MPa
Elongation at break (x-y plane)		1.5 ± 1%	1 ± 0.5%
Heat deflection temperature @ 0,46 MPa*	ASTM D648	132 °C (270 °F)	268 °C (514 °F)
Heat deflection temperature @ 1,82 MPa*		82 °C (180 °F)	119 °C (246 °F)

#### \*From supplier data sheet

### TOLERANCES

For well-designed parts, tolerances in the X/Y dimension of  $\pm 0.002$  in. (0.05mm) for the first inch plus  $\pm 0.001$  in./ in., and Z-dimension tolerances of  $\pm 0.005$  in. (0.127mm) for the first inch plus  $\pm 0.001$  in./in. (0.001mm/mm), can typically be achieved. Note that tolerances may change depending on part geometry.

Version 1.0 I December 2019



All of the figures contained on this data sheet are approximate and dependent on a number of factors, including but not limited to, machine and process parameters. The information provided is therefore not binding and not deemed to be certified.

Protolabs HQ, 5540 Pioneer Creek Dr., Maple Plain, MN 55359 USA