

STEREOLITHOGRAPHY PP-LIKE TRANSLUCENT WHITE

Current Supplier Material: [Somos 9120](#)

PRODUCT DESCRIPTION

PP-Like Translucent White is translucent in appearance. It's also the most flexible stereolithography material available with a flexural modulus of 1,600 MPa. Its mechanical properties are similar to the average values of injection-molded polypropylene except for a slightly lower elongation at break.

APPLICATIONS

PP-Like Natural is often used for medical device prototypes, electrical casings, fluid flow analysis parts, and automotive components.

KEY PRODUCT BENEFITS

- Translucent
- Semi-flexible
- Enhanced feature details

PROPERTIES

PROPERTY	TEST METHOD	VALUE
Color	-	White
Density in solid state*	@ 25 °C (77 °F)	1.13 g/cm ³
Water absorption (20 °C, 50% relative humidity)	ASTM D570	-
E-module (x-y plane)	ASTM D638, test speed 10mm/min.	1,600 ± 300 MPa
Tensile strength (x-y plane)		35 ± 5 MPa
Elongation at break (x-y plane)		25 ± 5%
Heat deflection temperature @ 0,46 MPa*	ASTM D648	61 °C (142 °F)
Heat deflection temperature @ 1,82 MPa*		52 °C (126 °F)

*From supplier data sheet

TOLERANCES

For well-designed parts, tolerances in the X/Y dimension of ± 0.002 in. (0.05mm) for the first inch plus ± 0.001 in./in., and Z-dimension tolerances of ± 0.005 in. (0.127mm) for the first inch plus ± 0.001 in./in. (0.001mm/mm), can typically be achieved. Note that tolerances may change depending on part geometry.



>>>BORN FOR GREAT FEELINGS<<<

+86 075523287576 / info@greefeemold.com

address: 805 Tong Fang center Shajing, Baoan, Zhong Xing Road Shenzhen, China, 51812

All of the figures contained on this data sheet are approximate and dependent on a number of factors, including but not limited to, machine and process parameters. The information provided is therefore not binding and not deemed to be certified.

© Proto Labs 1999-2020