



Bayblend® T65 XF

Covestro - Polycarbonates - Polycarbonate + ABS

Wednesday, December 8, 2021

General Information

Product Description

(PC+ABS)-Blend; Vicat/B 120 temperature = 120°C; improved flow compared with T65

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Flow		
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• FORD WSS-M4D684-B1 • FORD WSS-M4D924-B1 • GM GMW15581P-ABS+PC-T2	• GM GMW15581P-ABS+PC-T2 Color: 901510 Black • GM GMW15581P-ABS+PC-T5 • GM GMW15581P-ABS+PC-T5 Color: 901510 Black	• GM QK 000195 Type B Color: 901510 Black • GM QK 002412 Color: 901510 Black

ASTM & ISO Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density (73°F (23°C))	1.13 g/cm ³	1.13 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	18 cm ³ /10min	18 cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 2577
Across Flow : 500°F (260°C), 0.118 in (3.00 mm)	0.50 to 0.70 %	0.50 to 0.70 %	
Flow : 500°F (260°C), 0.118 in (3.00 mm)	0.50 to 0.70 %	0.50 to 0.70 %	
Water Absorption			ISO 62
Saturation, 73°F (23°C)	0.70 %	0.70 %	
Equilibrium, 73°F (23°C), 50% RH	0.20 %	0.20 %	
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	341000 psi	2350 MPa	ISO 527-1/1
Tensile Stress			ISO 527-2/50
Yield, 73°F (23°C)	7830 psi	54.0 MPa	
Break, 73°F (23°C)	6820 psi	47.0 MPa	
Tensile Strain			ISO 527-2/50
Yield, 73°F (23°C)	4.4 %	4.4 %	
Break, 73°F (23°C)	> 50 %	> 50 %	
Flexural Modulus ³ (73°F (23°C))	341000 psi	2350 MPa	ISO 178
Flexural Stress ³			ISO 178
3.5% Strain, 73°F (23°C)	10600 psi	73.0 MPa	
73°F (23°C)	12200 psi	84.0 MPa	

Copyright ©, 2021 Avient Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Avient Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Avient Distribution Company's direct control. Avient Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

Bayblend® T65 XF

Covestro - Polycarbonates - Polycarbonate + ABS

Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	17 ft·lb/in ²	36 kJ/m ²	
73°F (23°C)	24 ft·lb/in ²	50 kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-22°F (-30°C)	17 ft·lb/in ²	35 kJ/m ²	
73°F (23°C)	23 ft·lb/in ²	48 kJ/m ²	
Unnotched Izod Impact Strength			ISO 180
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			
66 psi (0.45 MPa), Unannealed	252 °F	122 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	216 °F	102 °C	ISO 75-2/A
Vicat Softening Temperature			
--	248 °F	120 °C	ISO 306/B120
--	244 °F	118 °C	ISO 306/B50
CLTE			ISO 11359-2
Flow : 73 to 131°F (23 to 55°C)	4.4E-5 in/in/°F	8.0E-5 cm/cm/°C	
Transverse : 73 to 131°F (23 to 55°C)	4.7E-5 in/in/°F	8.5E-5 cm/cm/°C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+16 ohms	1.0E+16 ohms	IEC 60093
Volume Resistivity (73°F (23°C))	1.0E+16 ohms·cm	1.0E+16 ohms·cm	IEC 60093
Electric Strength			IEC 60243-1
73°F (23°C), 0.0394 in (1.00 mm)	890 V/mil	35 kV/mm	
Relative Permittivity			IEC 60250
73°F (23°C), 100 Hz	3.10	3.10	
73°F (23°C), 1 MHz	3.00	3.00	
Dissipation Factor			IEC 60250
73°F (23°C), 100 Hz	3.0E-3	3.0E-3	
73°F (23°C), 1 MHz	8.5E-3	8.5E-3	
Comparative Tracking Index (Solution A)	250 V	250 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.03 in (0.9 mm))	HB	HB	UL 94
Oxygen Index ⁴	24 %	24 %	ISO 4589-2
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Melt Viscosity ⁵ (500°F (260°C))	200 Pa·s	200 Pa·s	ISO 11443-A
Additional Information	Typical Value (English)	Typical Value (SI)	
ISO Shortname	PC+ABS	PC+ABS	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature - Dry Air Dryer	203 to 230 °F	95 to 110 °C
Drying Time - Dry Air Dryer	4.0 hr	4.0 hr
Suggested Max Moisture	< 0.020 %	< 0.020 %
Suggested Shot Size	30 to 70 %	30 to 70 %
Rear Temperature	428 to 446 °F	220 to 230 °C

Copyright ©, 2021 Avient Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Avient Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Avient Distribution Company's direct control. Avient Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

Bayblend® T65 XF

Covestro - Polycarbonates - Polycarbonate + ABS

Injection	Typical Value (English)	Typical Value (SI)
Middle Temperature	437 to 455 °F	225 to 235 °C
Front Temperature	446 to 464 °F	230 to 240 °C
Nozzle Temperature	491 to 509 °F	255 to 265 °C
Processing (Melt) Temp	464 to 518 °F	240 to 270 °C
Mold Temperature	158 to 194 °F	70 to 90 °C
Back Pressure	725 to 2180 psi	5.00 to 15.0 MPa
Vent Depth	9.8E-4 to 3.0E-3 in	0.025 to 0.075 mm

Injection Notes

Peripheral Screw Speed: 0.05 - 0.2 m/s
Standard Melt Temperature: 260°C
Hold Pressure (% of Injection Pressure): 50 - 75%

Notes

¹ Typical properties: these are not to be construed as specifications.

² 150x105x3mm,, MT 80°C

³ 0.079 in/min (2.0 mm/min)

⁴ Procedure A

⁵ 1000s-1