



Hytrel® 3078

DuPont Transportation & Industrial - THERMOPLASTIC POLYESTER ELASTOMER

Wednesday, December 8, 2021

General Information

Product Description

30 Shore D High Performance Polyester Elastomer with Non-discoloring Stabilizer

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
RoHS Compliance	• Contact Manufacturer		
Automotive Specifications	• GM GMW15702-250037		
Part Marking Code (ISO 11469)	• >TPC-ET<		
Resin ID (ISO 1043)	• TPC-ET		

ASTM & ISO Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.07 g/cm ³	1.07 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.0 g/10 min	5.0 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	5.0 cm ³ /10min	5.0 cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.50 %	0.50 %	
Flow	0.80 %	0.80 %	
Water Absorption			ISO 62
24 hr, 73°F (23°C)	0.50 %	0.50 %	
Saturation, 73°F (23°C), 0.0787 in (2.00 mm)	0.80 %	0.80 %	
Equilibrium, 73°F (23°C), 0.0787 in (2.00 mm), 50% RH	0.20 %	0.20 %	
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress			ISO 527-2
10% Strain	261 psi	1.80 MPa	
50% Strain	725 psi	5.00 MPa	
Flexural Modulus	3920 psi	27.0 MPa	ISO 178
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tear Strength			ISO 34-1
Across Flow	440 lbf/in	77.0 kN/m	
Flow	457 lbf/in	80.0 kN/m	

Copyright ©, 2021 Avient Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Avient Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Avient Distribution Company's direct control. Avient Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

Hytrel® 3078

DuPont Transportation & Industrial - THERMOPLASTIC POLYESTER ELASTOMER

Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°F (-40°C)	No Break	No Break	
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Notched Izod Impact Strength			ISO 180/1A
-40°F (-40°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Shore Hardness			ISO 48-4
Shore D ²	30	30	
Shore D, 15 sec	26	26	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-144 °F	-98.0 °C	ISO 974
Glass Transition Temperature ³	-76.0 °F	-60.0 °C	ISO 11357-2
Melting Temperature ³	338 °F	170 °C	ISO 11357-3
CLTE			ISO 11359-2
Flow	9.8E-5 in/in/°F	1.8E-4 cm/cm/°C	
Transverse	1.1E-4 in/in/°F	2.1E-4 cm/cm/°C	
Effective Thermal Diffusivity	5.44E-8 mm ² /s	5.44E-8 mm ² /s	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+14 ohms	1.0E+14 ohms	IEC 62631-3-2
Volume Resistivity	1.0E+11 ohms·m	1.0E+11 ohms·m	IEC 62631-3-1
Electric Strength	460 V/mil	18 kV/mm	IEC 60243-1
Relative Permittivity			IEC 62631-2-1
1 MHz	5.30	5.30	
100 Hz	5.40	5.40	
Dissipation Factor			IEC 62631-2-1
100 Hz	7.0E-3	7.0E-3	
1 MHz	0.015	0.015	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Burning Rate ⁴ (0.0394 in (1.00 mm))	1.3 in/min	33 mm/min	ISO 3795
Flame Rating			UL 94
0.06 in (1.5 mm)	HB	HB	IEC 60695-11-10,
0.12 in (3.0 mm)	HB	HB	-20
Oxygen Index	19 %	19 %	ISO 4589-2
FMVSS Flammability	B	B	FMVSS 302
Fill Analysis	Typical Value (English)	Typical Value (SI)	
Melt Density	0.940 g/cm ³	0.940 g/cm ³	
Specific Heat Capacity of Melt	0.514 Btu/lb/°F	2150 J/kg/°C	
Thermal Conductivity of Melt	1.0 Btu·in/hr/ft ² /°F	0.15 W/m/K	

Copyright ©, 2021 Avient Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Avient Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Avient Distribution Company's direct control. Avient Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

Hytrel® 3078

DuPont Transportation & Industrial - THERMOPLASTIC POLYESTER ELASTOMER

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time - Desiccant Dryer	2.0 to 3.0 hr	2.0 to 3.0 hr
Suggested Max Moisture	< 0.080 %	< 0.080 %
Processing (Melt) Temp	374 to 410 °F	190 to 210 °C
Melt Temperature, Optimum	401 °F	205 °C
Mold Temperature	86 to 104 °F	30 to 40 °C
Mold Temperature, Optimum	86 °F	30 °C
Drying Recommended	yes	yes

Extrusion	Typical Value (English)	Typical Value (SI)
Drying Temperature	158 to 194 °F	70 to 90 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Suggested Max Moisture	< 0.060 %	< 0.060 %
Melt Temperature	374 to 401 °F	190 to 205 °C
Extrusion Melt Temperature, Optimum	392 °F	200 °C

Notes

¹ Typical properties: these are not to be construed as specifications.

² max

³ 10°C/min

⁴ FMVSS 302